

AD-A182 104

AD

AD-E401 703


TECHNICAL REPORT ARAED-TR-87020

**NON-NEWTONIAN LIQUID PROPELLANT (NNLP)
SENSITIVITY: PRELIMINARY STUDIES**

P. HUI
A. BRACUTI

JUNE 1987

STIC
SELECTED
JUL 02 1987
A



U.S. ARMY
ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER
PICATINNY ARSENAL, NEW JERSEY

**U. S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER
ARMAMENT ENGINEERING DIRECTORATE
PICATINNY ARSENAL, NEW JERSEY**

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

87 6 80 03
87

The views, opinions, and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

The citation in this report of the names of commercial firms or commercially available products or services does not constitute official endorsement by or approval of the U.S. Government.

Destroy this report when no longer needed by any method that will prevent disclosure of contents or reconstruction of the document. Do not return to the originator.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER TECHNICAL REPORT ARAED-TR-87020	2. GOVT ACCESSION NO. AD-A182104	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) NON-NEWTONIAN LIQUID PROPELLANT (NNLP) SENSITIVITY: PRELIMINARY STUDIES		5. TYPE OF REPORT & PERIOD COVERED Preliminary September 1986 - April 1987
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) P. Hui and A. Bracuti		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS ARDEC, AED Energetics and Warheads Div (SMCAR-AEE-BR) Picatinny Arsenal, NJ 07806-5000		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS ARDEC, IMD STINFO Div (SMCAR-MSI) Picatinny Arsenal, NJ 07806-5000		12. REPORT DATE June 1987
		13. NUMBER OF PAGES 21
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Non-Newtonian liquid propellants (NNLP) RDX, Gel propellants, (GP) azidoethanol (TAE), Liquid propellants, (LP) a Hot, fragments, conductive ignition, LOVA propellants, Impact, sensitivity, Triaminoguanidinium nitrate, (TAGN) Impact cavity, drop test, ←		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Samples of non-Newtonian liquid propellants containing various concentrations of RDX, TAGN, and TAE tested for sensitivity to impact, friction and electrostatic discharge, and hot fragments (vulnerability) were compared against similar test results obtained from solid propellants (M30 and XM39 LOVA) and liquid propellants (NOS 365 and OTTO Fuel II). The data indicated that high energy non-Newtonian liquid propellants can be safely processed. Keywords: ✓		

ACKNOWLEDGEMENT

The authors wish to acknowledge the assistance of the following personnel for their contributions to this technical report: K. Wagaman of Naval Surface Weapons Center, Maryland and E. Walsman of Naval Ordnance Station/Indian Head, Maryland.

Accession For		20
NTIS GRA&I	<input checked="" type="checkbox"/>	
DTIC TAB	<input type="checkbox"/>	
Unannounced	<input type="checkbox"/>	
Justification		
By		
Distribution /		
Availability Codes		
Avail and/or		
Dist Special		
Al		

CONTENTS

	Page
Introduction	1
Experimental	1
Impact Test	2
Impact Cavity Drop Test	2
Electrostatic Discharge	2
Sliding Friction Test	3
Hot Fragment Conductive Ignition Test	3
Results	3
Conclusions and Recommendations	4
References	11
Distribution List	13

TABLES

1 Gel propellant composition and thermochemistry	5
2 Impact sensitivity test results	6
3 Range of sensitivity	7
4 Electrostatic discharge test data	8
5 Friction sensitivity test data	9
6 Hot fragment conductive ignition test	10

INTRODUCTION

A propellant may be defined as an energetic material that will **safely** provide the necessary **force** to hurl a projectile swiftly and accurately to a specific target. Of the two goals, safety is more important and quite often a more difficult achievement. As a result, specific laboratory safety tests have been devised for materials which categorize propellants with respect to sensitivity to various stimuli. Materials displaying sensitivity levels that exceed prescribed "safe" limits can be either eliminated from further consideration or modified in some way to make them conform to acceptable sensitivity standards.

The purpose of this study is to screen a few experimental gel propellant (GP) formulations which are special types of non-Newtonian propellants for sensitivity to impact, friction, electrostatic discharge, and hot fragment conductive ignition (vulnerability) in order to guide future formulation efforts. Unfortunately, since no experimental data base for gel propellants is currently available, sensitivity data acquired from selected solid and liquid propellants had to be used as the initial basis of comparison.

These particular GP formulations contain two major ingredients, solid oxidizer and energetic liquid (fuel), and a minor ingredient which for convenience shall be referred to as a gelling agent. In the course of propellant processing, one or more solid oxidizers are dispersed into the energetic liquid with the aid of a modicum of gelling agent. The purpose of the addition of gelling agent is to ensure propellant structure stability. In a previous GP study (ref 1), the selected gel propellants were formulated with triaminoguanidinium nitrate (TAGN) and cyclotrimethylenetrinitramine (RDX) as the oxidizers and with either 2-azidoethanol (TAE) or bis (2,2-dinitropropyl) acetal-formal (BDNPA-F) as the energetic liquids.

The referenced investigation demonstrated that GP containing BDNPA-F displayed color changes during a six-month storage period which is indicative of potentially unstable properties and low combustion rates which did not meet targeted requirements. As a result, BDNPA-F was considered unsuitable for use in GP formulations and, accordingly, was eliminated from this program.

The GP candidates discussed in the present study feature only TAE as the energetic liquid, because TAE did not display any of the problems observed with BDNPA-F. The compositions, energy levels, and flame temperatures for the GP candidates are presented in table 1.

EXPERIMENTAL

Because the baseline of the sensitivity tests for gel propellants has not been established, the conventional solid propellant sensitivity evaluation tests were employed to screen gel propellant candidate. These tests include impact, impact cavity drop, sliding friction, electrostatic discharge and hot fragment conductive ignition tests. Impact testing was performed by both the laboratories of the Army at ARDEC, Picatinny Arsenal, NJ and the Navy Safety Office at Naval Ordnance Station (NOS), Indian Head, MD. The hot fragment conductive ignition test was conducted at ARDEC. All other tests, including the impact cavity drop, sliding friction, and electrostatic discharge were performed at NOS.

Impact Test

The impact sensitivities of several GP samples were measured by a standard technique in order to compare the results with values obtained with reference energetic materials. Impact sensitivity is defined as the minimum impact energy required to ignite a propellant or explosive. In general, it is measured in the laboratory by determining the minimum distance a given weight must fall onto an energetic material to induce ignitions.

At ARDEC, testing was conducted with an Explosive Research Laboratory (ERL) type 12 impact tester, which uses a 2.5-kg steel drop weight and a 30-mg sample placed on sand paper positioned between two steel anvils. The drop height corresponding to 50% probability of initiation measured by means of the Bruceton up-and-down method is used as a measure of impact sensitivity. The criterion for initiation was the observation of either burning or deflagration upon impact of the sample. A detailed description of the apparatus is contained in reference 2.

Although the NOS Safety Office employs a similar technique for the impact test with the Drop-Weight tester, there are specific differences such as a heavier drop weight (5.0 kg) and a smaller sample size (20 mg). The data are reported as the minimum drop height required to produce three successive initiations. A description of the apparatus is contained in reference 3.

Impact Cavity Drop Test

Impact cavity drop testing was also performed by NOS using a similar technique in which a 0.03-ml sample was placed in a cup rather than on sand paper positioned between two steel anvils. In this case, 2.0-kg drop weight was substituted for the 5.0-kg one. The test results were reported as the drop heights at which initiation is 50% probable. In this test, propellants are initiated by a complex compression mechanism involving propellant pressurization rate, heat transfer, thermodynamic gas/liquid properties, and hydrodynamic properties. Although the significance of this test is not fully understood, it is a useful, simple, and rapid laboratory tool to compare the sensitivities of nonsolid propellants on a relative scale. The test method and procedures used in this test are employed and recommended by the majority of the liquid propellant community as a standardized test technique (ref 4).

Electrostatic Discharge

The electrostatic sensitivity tests performed at NOS determine the minimum electrostatic discharge energy required to ignite the sample. This is accomplished with an approaching electrode apparatus in which electrostatic energy is stored in a capacitor connected to the electrode. The capacitor is allowed to discharge into the sample at varying energy levels. The minimum electrostatic energy required to achieve ignition is then determined. If any evidence of combustion is observed such as the generation of smoke, flame, odor, or noise, the test is considered positive. Discharge energy is then adjusted until 20 consecutive positive tests can be achieved. A detailed description of this apparatus is contained in reference 3.

Sliding Friction Test

The sliding friction sensitivity test (ref 3) determined the minimum frictional energy required to ignite propellant samples. In this test procedure, a 50-mg sample is placed between a block and a wheel that is attached to a hydraulic ram which adjusts the force on the sample surface. A pendulum of selected weight is then allowed to strike the end of the block which causes the wheel to roll over the sample with a known frictional force. The maximum frictional force is then determined and can be applied to the sample without causing decomposition.

Hot Fragment Conductive Ignition Test

Hot fragment conductive ignition (HFCI) tests were performed to compare the relative vulnerability of the samples to ignition by an imbedded hot steel fragment. This test was developed by the Ballistic Research Laboratory as an experimental technique to screen new propellant formulations for vulnerability. The results give a crude approximation to the large-scale vulnerability test such as shaped-charge jet generated spall test which simulates one of the principal threats faced by tank systems during combat (refs 5, 6, and 7). The HFCI test was designed to model the conductive ignition from spall and to obtain a quantitative measure of a propellant's susceptibility to ignition stimuli.

In this test, a steel ball is heated in a tube furnace to preselect temperature and then dropped onto a propellant bed (approximately 10 grams) housed in a small glass beaker maintained at ambient conditions. The response of the propellant to this external stimuli is determined by observing if ignition occurs. The temperature is then raised or lowered by a 25°C increment depending on the response of the propellant. The test is iterated until the transition between ignition and nonignition is defined. Four fragments ranging from 0.43 g to 3.50 g were selected in this test to cover the spectrum of spall sizes most commonly generated by shaped charges.

RESULTS

Impact sensitivity data for GP samples tested at ARDEC (lots 7117 and 7117A) and at NOS (lots 7136, 7137, and 7138) (table 2) reveal that all the GP samples are less sensitive to impact than their referenced counterparts. In fact, the NOS tests indicate that the GP impact sensitivities equal or surpass the sensitivity limit (600 mm) of the NOS impact sensitivity device. Based on the NOS impact sensitivity guidelines (table 3), GP samples (lots 7136, 7137, and 7138) should be classified as having the lowest impact sensitivity. The other lots cannot be ranked on this scale because they were not tested under the same conditions (5.0 kg drop weight). However, all GP samples are significantly less sensitive than RDX and high energy LOVA propellant as indicated.

Impact cavity drop test data (table 2) indicate that the tested GP samples (lot 7136, 7137, and 7138) are all in the low sensitive region (table 3) and half as sensitive to impact than the known liquid propellant (LP) Otto Fuel II. Therefore, based on the results of the impact and the impact cavity drop test, it is suggested that gel propellants are insensitive to impact and are safe to handle in the propellant processing.

The electrostatic discharge data (table 4) indicate that 50-mg samples from lots 7136, 7137, and 7138 required 8.75, 6.25, and 2.75 joules, respectively, to achieve ignition. These values fall within the NOS low electrostatic sensitivity range of 1.125 to 12.55 joules (table 3) which suggest along with those values previously reported (ref 1) that no extreme electrostatic hazard exists in processing these gel propellants.

The data for friction sensitivity (table 5) indicate that GP samples 7136, 7137, and 7138 all fall within the low friction sensitivity range (750 to 1000 lb) with sliding friction values greater than 980 lb which is also the upper limit of the NOS friction testing device.

The vulnerability data (table 6) comparing gel propellants with M30 and standard LOVA XM39 solid propellants and NOS 365 and HAN 1845 liquid propellants indicate that all gel propellants tested were less sensitive than M30. GP samples 7121A, 7136, 7137, and 7138 were less vulnerable than XM39 LOVA and comparable to NOS 365 and HAN 1845 liquid propellants while the remainder were more vulnerable than XM39 LOVA and the liquid propellants.

CONCLUSIONS AND RECOMMENDATIONS

Although the data in this report are by no means comprehensive, the impact, friction, and electrostatic test results do, however, suggest that highly energetic gel propellants can be fabricated, processed, and handled safely. In addition, the vulnerability data indicate that highly energetic propellants of this type may well serve as high energy substitutes for solid LOVA propellants.

Future studies should include an investigation of the effect of oxidizer particle size on GP sensitivity and a comprehensive investigation on the effects of different gelling agents on GP properties.

Finally, testing techniques for nonsolid propellants (LP/GP) should be standardized and the results normalized to a meaningful standard scale.

Table 1. Gel propellant composition and thermochemistry

LOT	7117	7117A	7121A	7136	7137	7138
TAGN	20.0	30.0	23.3	10.0	10.0	10.0
RDX	40.0	30.0	45.6	50.0	55.0	55.0
TAE	40.0	40.0	31.1	40.0	35.0	33.6
AMMONIUM NITRATE	--	--	--	--	--	1.4
METHOCEL HB	1.0	1.0	--	--	--	--
ETHOCEL 10	--	--	0.5	0.5	0.5	0.5
IMPETUS, J/g	1165	1129	1205	1185	1223	1229
TEMP. K	2602	2479	2774	2707	2854	2888

Table 2. Impact sensitivity test results

Lot	ARDEC	NOS	
	2.5 Kg Wt [*] (mm)	5.0 Kg Wt ^{**} (mm)	Cavity Drop 2.0 Kg Wt [*] (mm)
RDX (CL-E)	230	150	---
HE LOVA II	448	300	---
OTTO II	---	---	105
7117	807	---	---
7117A	780	---	---
7136	---	600	239
7137	---	>600	304
7138	---	>600	208

* Height at which initiation is 50% probable

** Lowest height yielding 3 consecutive positive

Table 3. Range of sensitivity

TEST	RANGE		
	HIGH	MEDIUM	LOW
IMPACT, ¹ mm FRICTION ²	0-75	100-325	350-600
PROPELLANT, Lb	0-55	75-560	750-1000
INGREDIENT, Lb	0-30	40-420	560-1000
ELECTROSTATIC, ³ J	0.00125-0.00875	0.0125-0.865	1.125-12.5
CAVITY DROP, ⁴ mm	0-34	35-80	>80

NOTE:

1. 5.0 Kg DROP WEIGHT, LOWEST HEIGHT YIELDING 3 CONSECUTIVE POSITIVES
2. 8 ft/sec VELOCITY, MAXIMUM HEIGHT YIELDING 20 CONSECUTIVE NEGATIVES
3. 5 KV, MAXIMUM HEIGHT YIELDING 20 CONSECUTIVE NEGATIVES
4. 2.0 Kg DROP WEIGHT, HEIGHT AT WHICH INITIATION IS 50% PROBABLE

Table 4. Electrostatic discharge test data

<u>Lot</u>	<u>Discharge Energy @ 5 KV (joule)</u>	<u>Sensitivity Range</u>
7136	8.75	Low
7137	6.25	Low
7138	2.75	Low

Table 5. Friction sensitivity test data

<u>Lot</u>	<u>Sliding Friction</u> @ 8 ft/sec (Lb _f)	<u>Sensitivity</u>
7136	>980	negative
7137	>980	negative
7138	>980	negative

Table 6. Hot fragment conductive ignition test

LOT	FRAGMENT WEIGHT (g)			
	0.43	1.03	2.03	3.50
	IGNITION TEMPERATURE (c)			
M30	363	338	313	288
LOVA STD	788	663	563	463
7117	488	463	388	363
7117A	538	488	438	413
7121A	>800	713	488	438
7136	>800	788	638	588
7137	>800	738	538	488
7138	788	763	688	488

NOTE: ABOUT 10g SAMPLE FOR EACH RUN

REFERENCES

1. Hui, P., Bracuti, A. J., and Chiu, D., "Fundamental Studies on Experimental Nonnewtonian Liquid Propellant (NNLP)," 1986 JANNAF Propulsion Meeting, CPIA Publication 455, Vol. I, pp. 137-147, August 1986.
2. Walker, G. R., "Manual of Sensitiveness Tests," (AD-824359) TTCP Panel 0-2 (Explosives), Canadian Armament Research and Development Establishment, Valeartier, Quebec, Canada, February 1966.
3. Wright, K. D., and et al. "Preliminary Hazards Analysis for the Twin-Screw Extruder Facility," LHSP 86-214, Naval Ordnance Station, Indian Head, MD, May 1986.
4. "Drop-Weight Tests, Liquid Propellant Test Methods, Test Number 4," JANNAF ICRPG Working Group on Liquid Propellant Test Methods, CPIA Publication, May 1964.
5. Gerri, N. J., "Vulnerability Assessment Methodology for Candidate LOVA Propellants," Proceedings of the 1980 JANNAF Propulsion System Hazards Subcommittee, CPIA Publication 330, December 1980.
6. Wise, S., Rocchio, J. J., and Reeves, H. J., "Propellant Binder Chemistry and Sensitivity to Thermal Threat," Proceedings of the 1980 JANNAF Propulsion Systems Hazards Subcommittee Meeting, CPIA Publication 330, December 1980.
7. Law, H. C. and Rocchio, J. J., "The Hot Fragment Conductive Ignition Test: A Means of Evaluating Propellant Vulnerability to Spall," 1981 JANNAF Combustion Meeting, October 1981.

DISTRIBUTION LIST

Commander
Armament Research, Development
and Engineering Center
U.S. Army Armament, Munitions
and Chemical Command
ATTN: SMCAR-MSI (5)
SMCAR-AEE (3)
SMCAR-AEE-BR, D. S. Downs
A. J. Beardell
Y. Carignan
P. Hui (10)
A. Bracuti (5)
SMCAR-ARR-WE, C. Knapp
M. Kirshenbaum
T. Dolch
SMCAR-SFS
SMCAR-FSD
Picatinny Arsenal, NJ 07806-5000

Commander
U.S. Army Armament, Munitions
and Chemical Command
ATTN: AMSMC-GCL(D)
Picatinny Arsenal, NJ 07806-5000

Administrator
Defense Technical Information Center
ATTN: Accessions Division (I2)
Cameron Station
Alexandria, VA 22304-6145

Director
U.S. Army Materiel Systems
Analysis Activity
ATTN: AMXSY-MP
Aberdeen Proving Ground, MD 21005-5066

Commander
Chemical Research, Development
and Engineering Center
U.S. Army Armament, Munitions
and Chemical Command
ATTN: SMCCR-MSI
Aberdeen Proving Ground, MD 21010-5423

Commander
Chemical Research, Development
and Engineering Center
U.S. Army Armament, Munitions
and Chemical Command
ATTN: SMCCR-RSP-A
Aberdeen Proving Ground, MD 21010-5423

Director
Ballistic Research Laboratory
ATTN: AMXBR-OD-ST
Aberdeen Proving Ground, MD 21005-5066

Chief
Benet Weapons Laboratory, CCAC
Armament Research, Development
and Engineering Center
U.S. Army Armament, Munitions and Chemical Command
ATTN: SMCAR-CCB-TL
SMCAR-LCB-DS, A. Graham
Watervliet, NY 12189-5000

Commander
U.S. Army Armament, Munitions and
Chemical Command
ATTN: SMCAR-ESP-L
SMCAR-IRC, G. H. Cowan
SMCAR-LC
SMCAR-LEM, W. D. Fortune
R. Zastrow
SMCAR-SF, L. Smith
Rock Island, IL 61299-6000

Director
U.S. Army TRADOC Systems
Analysis Activity
ATTN: ATAA-SL
White Sands Missile Range, NM 88002

Director
Ballistics Research Laboratory
U. S. Army Laboratory Command
ATTN: SLCBR-IB, I. May
SLCBR-TSB-S
Aberdeen Proving Ground, MD 21005-5066

Commander
U.S. Army Materiel Command
ATTN: DRCSF-E, Safety Office
5001 Eisenhower Avenue
Alexandria, VA 22333

Chairman
DoD Explosives Safety Board
Room 856-C
Hoffman Bldg 1
2461 Eisenhower Avenue
Alexandria, VA 22331

Commander
U.S. Army Training and Doctrine Command
ATTN: ATCD-MA, Maj Williams
Fort Monroe, VA 23351

Office of the Under Secretary of Defense
Research and Engineering
Washington, DC 20301

Headquarters, Department of the Army
ATTN: SAUS-OR, D. Hardison
Washington, DC 20301

Headquarters, Department of the Army
ATTN: DAMI-ZA
DAMI-CSM
SARD
Washington, DC 21310

Commander
U.S. Army Tank-Automotive Command
Warren, MI 48090

Project Manager
Tank Main Armament Systems
ATTN: AMCPM-TMA, K Russell
AMCPM-TMA-105
AMCPM-120
Picatinny Arsenal, NJ 07806-5000

Project Manager
U.S. Army Tank-Automotive Command
Improved TOW Vehicle/Fire Support
Team Vehicle
ATTN: DRCPM-ITV
Warren, MI 48090

Commandant
U.S. Army Infantry School
ATTN: Infantry Agency
Fort Benning, GA 31095

U.S. Army Armor and Engineer Board
ATTN: STEBB-AD-S
Fort Knox, KY 40121

Commandant
U.S. Army Aviation Center
ATTN: Aviation Agency
Fort Rucker, AL 36362

Project Manager
U.S. Army Tank-Automotive Command
M60 Tanks
ATTN: DRCPM-M60-T
Warren, MI 48090

Commander
U.S. Army Logistics Management Center
Defense Logistics Studies
Fort Lee, VA 23801

Commander
U.S. Army Mobility Equipment
Research and Development Command
ATTN: DRDME-WC
Fort Belvoir, VA 22060

Program Manager
M1 Tank System
U.S. Army Tank-Automotive Command
ATTN: DRCPM-GCM-SA, J. Roossien
Warren, MI 48090

Commander
U.S. Army Mobility Equipment Command
4300 Goodfellow Blvd
St. Louis, MO 63120

AFFDL
ATTN: TST-Lib
Wright-Patterson AFB, OH 45433

AFATL
ATTN: DLYV
Eglin AFB, FL 32542

Chief of Naval Materiel
Department of the Navy
ATTN: J. A. Amlie
Washington, DC 20360

Commander
Naval Air System Command
ATTN: NAIR-954 Technical Library
Washington, DC 20361

Strategic Systems Project Office
Department of the Navy
Room 901
ATTN: J. F. Kincaid
Washington, DC 20376

Commander
U.S. Naval Surface Weapons Center
ATTN: Code G33, J. L. East
Code DX-21 Technical Library
Dahlgren, VA 22448

Commander
U. S. Naval Weapons Center
ATTN: A. T. Nielson
Info Sci Div
China Lake, CA 93555

Chief, Naval Research
ATTN: Code 473, R. S. Miller
800 N. Quincy Street
Arlington, VA 22217

Project Manager
U. S. Army Tank-Automotive Command
Fighting Vehicle Systems
ATTN: DRCPM-FVS
Warren, MI 48090

Commanding General
U. S. Army Armor Center and Fort Knox
ATTN: ATZK-CD-MS, M. Falkovitch
Fort Knox, KY 40121

Director
U. S. Army Materials and Mechanics
Research Center
ATTN: DRXMR-D
Watertown, MA 02172

Commandant
U. S. Army Special Warfare School
ATTN: Rev & Tng Lit Div
Fort Bragg, NC 28307

ADTC
ATTN: DLOSL Tech Library
Eglin AFB, FL 32542

AFRPL

ATTN: B.B. Goshgarian
Technical Library
D. Thrasher
N. VanderHyde
Edwards AFB, CA 93523

AFSC

Andrews AFB
Washington, DC 20331

AFFTC

ATTN: SSD-Technical Library
Edwards AFB, FL 93523

Commander

U. S. Naval Surface Weapons Center
ATTN: S. J. Jacobs/Code 240
Technical Library
R. R. Bernecker
H. Addph Code R-10
K. Wagaman
Silver Spring, MD 20910

Commanding Officer

U.S. Naval Ordnance Station
ATTN: E. Walsman
Technical Library
Indian Head, MD 20604

Superintendent

U.S. Naval Postgraduate School
ATTN: Code 1424 Library
Monterey, CA 93940

Commanding Officer

Naval Underwater Systems Center
ATTN: Technical Library
Newport, RI 02840

Commander

U.S. Naval Surface Weapons Center
ATTN: J. P. Consaga
C. Gotzmer
Indian Head, MD 20640

Commander
U.S. Naval Sea Systems Command
ATTN: NAVSEA-0331, J. W. Murrin
R. Beauregard
National Center, Bldg 2
Room 6E08
Washington, DC 20360

Naval Research Laboratory
Technical Library
Washington, DC 20375

John Hopkins University
Applied Physics Laboratory
Chemical Propulsion Information Agency
ATTN: T. Christian
H. H. Gege
J. Hannum
John Hopkins Road
Laurel, MD 20810

NASA Headquarters
600 Independence Avenue, SW
ATTN: Code JM6, Technical Library
Washington, DC 20546

NASA/Lyndon B. Johnson Space Center
ATTN: NHS-22, Library Section
Houston, TX 77058